

LNP™ THERMOTUF™ COMPOUND VX99809

PDX-V-99809
REGION AMERICAS

DESCRIPTION

LNP THERMOTUF VX99809 is a compound based on Super Tough Nylon resin containing Proprietary Filler(s). Added feature of this material is: High Impact.

TYPICAL PROPERTY VALUES

Revision 20170816

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	43	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	40	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.9	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	75.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	1980	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	1220	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	42	MPa	ISO 527
Tensile Stress, break, 5 mm/min	41	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.6	%	ISO 527
Tensile Strain, break, 5 mm/min	129	%	ISO 527
Tensile Modulus, 1 mm/min	1880	MPa	ISO 527
Flexural Modulus, 2 mm/min	1300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1330	J/m	ASTM D 4812
Izod Impact, notched, 23°C	885	J/m	ASTM D 256
Multiaxial Impact	49	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	145	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	82	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	178	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	49	°C	ASTM D 648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	100	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	47	°C	ISO 75/Af

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Density	1.084	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.92	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	2 – 3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	2 – 3	%	ASTM D 955
Density	1.08	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.9	%	ISO 62
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	280 – 295	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	275 – 290	°C	
Rear - Zone 1 Temperature	260 – 270	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.