

LubriOne™ LB9220-5001 RS LB NATURAL 70

Polyphenylene Sulfide

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Europe	
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight		
Features	• Good Impact Resistance • Good Stiffness • Good Strength	• Heat Stabilized • Low Friction • Lubricated	• Wear Resistant
Uses	• Appliances • Automotive Applications	• Consumer Applications • Electrical/Electronic Applications	• General Purpose • Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.75 g/cm ³	1.75 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	2.18E+6 psi	15000 MPa	ISO 527-2
Tensile Stress	21800 psi	150 MPa	ISO 527-2/5
Tensile Strain (Break)	1.5 %	1.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	2.9 ft·lb/in ²	6.0 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature (DSC)	572 to 626 °F	300 to 330 °C	ISO 3146
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	248 to 284 °F	120 to 140 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	599 to 617 °F	315 to 325 °C
Middle Temperature	608 to 626 °F	320 to 330 °C
Front Temperature	617 to 635 °F	325 to 335 °C
Nozzle Temperature	626 to 644 °F	330 to 340 °C
Mold Temperature	275 to 311 °F	135 to 155 °C

Notes

¹ Typical values are not to be construed as specifications.

² 0.039 in/min (1 mm/min)

Copyright © 2023 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com