



Luran® S 757G

INEOS Styrolution - Acrylonitrile Styrene Acrylate

Sunday, November 3, 2019

General Information

Product Description

Luran® S 757G provides the best flowability within the product line and is therefore in particular suitable for demanding injection molding geometries.

FEATURES

- Highest flowability
- Easy processing

APPLICATIONS

- Household and sanitary appliances
- Motor bicycle parts

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Processability	• High Flow	
Uses	• Appliances	• Household Goods	• Sanitary Products
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	25	cm ³ /10min	ISO 1133
Molding Shrinkage ²	0.40 to 0.70	%	ISO 294-4
Water Absorption (Saturation, 73°F)	1.7	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.35	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	348000	psi	ISO 527-2
Tensile Stress (Yield, 73°F)	7400	psi	ISO 527-2
Tensile Strain (Yield, 73°F)	3.3	%	ISO 527-2
Nominal Tensile Strain at Break (73°F)	8.0	%	ISO 527-2
Tensile Creep Modulus (1000 hr)	239000	psi	ISO 899-1
Flexural Stress (73°F)	10900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	1.4	ft·lb/in ²	
73°F	5.7	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	13100	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (66 psi, Annealed)	214	°F	ISO 75-2/B
Heat Deflection Temperature ³ (264 psi, Annealed)	205	°F	ISO 75-2/A

Luran® S 757G

INEOS Styrolution - Acrylonitrile Styrene Acrylate

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	221	°F	ISO 306/A50
--	207	°F	ISO 306/B50
CLTE - Flow	4.4E-5 to 6.1E-5	in/in/°F	ISO 11359-2
Thermal Conductivity	1.2	Btu·in/hr/ft²/°F	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.40		
1 MHz	3.20		
Dissipation Factor			IEC 60250
100 Hz	0.010		
1 MHz	0.025		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		IEC 60695-11-10

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	464 to 536	°F
Mold Temperature	104 to 176	°F
Injection Velocity	472	in/min

Notes

¹ Typical properties: these are not to be construed as specifications.

² Free, longitudinal

³ 4h/80°C