



Lustran® Elite 1891

INEOS Styrolution - Acrylonitrile Butadiene Styrene

Sunday, November 3, 2019

General Information

Product Description

Lustran® Elite 1891 resin is an injection molding grade of ABS (acrylonitrile butadiene styrene) for high-heat applications in the automotive market. It provides high heat resistance, low gloss, toughness, and easy flow for processing molded-in color parts.

FEATURES

- SAE J1685: ABS0111
- High heat resistance
- Low gloss
- Easy flow
- UL 94 HB rated

APPLICATIONS

- AB pillars
- Door panels
- Console and console trim
- Lamp housings

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	• Good Flow • Good Toughness • High Heat Resistance • Low Gloss
Uses	• Automotive Applications • Automotive Interior Parts
Agency Ratings	• SAE J1685
Automotive Specifications	• CHRYSLER MS-DB-191 CPN3446 • CHRYSLER MS-DB-191 Type B CPN3346 Color: 90% Color Match • CHRYSLER MS-DB-191 Type B CPN3395 Color: Black • CHRYSLER MS-DB-191 Type B CPN3445 Color: Color Match • CHRYSLER MS-DB-191 Type B CPN3447 Color: Natural • CHRYSLER MS-DB-191 Type B CPN507 Color: Natural • DAIMLER DBL 5404.41 • FORD WSB-M4D690-A • FORD WSS-M4D690-B1 • GM GMP.ABS.009 • GM GMW15572P-ABS-T2 • SAE J1685 ABS0132 • TOYOTA TSM 5512G-2B • VOLKSWAGEN TL 527 Type B
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183

Lustran® Elite 1891

INEOS Styrolution - Acrylonitrile Butadiene Styrene

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR)			ISO 1133
220°C/10.0 kg	7.0	g/10 min	
230°C/3.8 kg	2.0	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 73°F)	6530	psi	ISO 527-2
Flexural Modulus (73°F)	329000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)			ASTM D256
-40°F	3.62	ft·lb/in ²	
73°F	7.95	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	4.4E-5	in/in/°F	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Mold Temperature	113 to 149	°F
Screw L/D Ratio	20.0:1.0	
Screw Compression Ratio	2.5:1.0	

Notes

¹ Typical properties: these are not to be construed as specifications.