

Alathon® M6060

High Density (MMW) Polyethylene

LyondellBasell Industries

Technical Data

Product Description

ALATHON M6060 is a medium molecular weight high density homopolymer with extremely low gel content. This resin provides high stiffness and narrow molecular weight distribution for use in cast film applications. Typical applications for this resin are dry food packaging, overwrap and WVTR.

General

Material Status	• Commercial: Active		
Literature ¹	• Processing - Mold Shrink (English) • Processing - Polyolefin Injection Molding Guide (English) • Processing - Start-Up Guide (English) • Technical Datasheet (English)		
Search for UL Yellow Card	• LyondellBasell Industries • Alathon®		
Availability	• Asia Pacific • Europe	• North America • South America	
Features	• Food Contact Acceptable • High Stiffness	• Homopolymer • Low Gel	• Narrow Molecular Weight Distribution
Uses	• Cast Film • Film	• Food Packaging • Packaging	
Agency Ratings	• FDA 21 CFR 177.1520		
Forms	• Pellets		
Processing Method	• Cast Film		

Physical	Nominal Value Unit	Test Method
Density	0.960 g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0 g/10 min	ASTM D1238

Films	Nominal Value Unit	Test Method
Secant Modulus		ASTM D882
MD	793 MPa	
TD	1030 MPa	
Tensile Strength		ASTM D882
MD: Yield	24.1 MPa	
TD: Yield	25.5 MPa	
Tensile Elongation		ASTM D882
MD: Break	850 %	
TD: Break	650 %	

Extrusion	Nominal Value Unit
Melt Temperature	199 °C

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.