

Technical Data Sheet

Microthene MU76000

Ethylene Vinyl Acetate



Product Description

Microthene G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. *Microthene* G powders combine the unique properties of a polyolefin resin with a small ground particle size.

Regulatory Status

For regulatory compliance information, see *Microthene* MU76000 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Colour Concentrates; Industrial; Interior Automotive Applications; Structural Parts
Market	Consumer Products; Flexible Packaging; Healthcare; Industrial, Building & Construction
Processing Method	Powders

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Equivalent Melt Index	32	g/10 min	32	g/10 min	ASTM D1238
Density, (23 °C)	0.941	g/cm ³	0.941	g/cm ³	ASTM D1505
Vinyl Acetate Content	18	%	18	%	LYB Method
Mechanical					
Tensile Strength at Break	1360	psi	9.4	MPa	ASTM D638
Tensile Elongation at Break	760	%	760	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	30		30		ASTM D2240
Thermal					
Vicat Softening Point	129	°F	54	°C	ASTM D1525
Low Temperature Brittleness	<-105	°F	<-76	°C	ASTM D746
Peak Melting Point	185	°F	85	°C	ASTM D3418
Additional Information					
Particle Shape	Irregular		Irregular		LYB Method
Average Particle Size	35	mesh	35	mesh	LYB Method

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

The small size and irregular shape of *Microthene* G powders facilitate dispersion with other components.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.