

OnFlex™ HT 65A-3E2102 black UV

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™ HT thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds is specially formulated to deliver very good compression set performance at elevated temperatures and a high heat resistance. Furthermore, OnFlex™ HT compounds offer excellent mechanical properties, a wide hardness range and good processability.

- Improved UV stability

General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Europe	• North America
Features	• High Heat Resistance • Low Compression Set	• Ozone Resistant • UV Stabilized	
Uses	• Automotive Exterior Parts		
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.00 g/cm ³	1.00 g/cm ³	ISO 1183
Molding Shrinkage - Flow ² 0.0787 in (2.00 mm), Injection Molded	0.017 in/in	1.7 %	Internal Method
Molding Shrinkage - Across Flow ² 0.0787 in (2.00 mm), Injection Molded	0.014 in/in	1.4 %	Internal Method
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ³			ISO 37
Across Flow : Break	1600 psi	11.0 MPa	
Flow : Break	1230 psi	8.50 MPa	
Tensile Elongation ³			ISO 37
Across Flow : Break	950 %	950 %	
Flow : Break	700 %	700 %	
Tear Strength	206 lbf/in	36.0 kN/m	ISO 34-1
Compression Set			ISO 815
73°F (23°C), 72 hr	24 %	24 %	
158°F (70°C), 22 hr	37 %	37 %	
212°F (100°C), 22 hr	46 %	46 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A, 10 sec)	65	65	ISO 48-4
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec ⁻¹	68.0 Pa·s	68.0 Pa·s	
392°F (200°C), 11200 sec ⁻¹	14.0 Pa·s	14.0 Pa·s	

Copyright © 2023 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	Styrenic Thermoplastic Elastomer (TES)	
Weather Resistance ⁴	expected to pass PV 3929	expected to pass PV 3929	Internal Method
Properties are measured using injection molded plaques.			

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Fast	Fast

Notes

¹ Typical values are not to be construed as specifications.

² Sign convention:

Positive shrinkage factor: Ejected part is smaller than the mould cavity. Shrinkage after processing is dependent on tool design, wall thickness and processing conditions.

Due to the multitude of factors influencing shrinkage during the processing users should only treat this as a guide and should make their own assessment.

Generally, low processing temperatures will cause an increase in shrinkage of up to 1% (direction of flow). Part geometry may further influence shrinkage by gradually releasing strain.

This may be accelerated by the annealing of parts, such as for 1hr at 80 °C.

³ 7.9 in/min (200 mm/min)

⁴ UV-Package successfully tested acc. to PV 3929 (Kalahari-Test) on a 60 Sh A Version.

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com