

## Technical Data Sheet

### Percom KCT40 GREY 6-2872



Polypropylene Copolymer

#### Product Description

Percom KCT40 GREY 6-2872 is a Polypropylene Copolymer Talc, 40% filled material and is typically used in Injection Molding applications. Features include: Copolymer.

#### Regulatory Status

For regulatory compliance information, see KCT40 GREY 6-2872 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

|                             |                                                                        |
|-----------------------------|------------------------------------------------------------------------|
| <b>Status</b>               | Limited Issue                                                          |
| <b>Availability</b>         | Africa-Middle East; Asia-Pacific; Europe; Latin America; North America |
| <b>Processing Method</b>    | Injection Molding                                                      |
| <b>Attribute</b>            | Copolymer                                                              |
| <b>Application</b>          | Appliance Components; Housings                                         |
| <b>Filler/Reinforcement</b> | Talc, 40%                                                              |

| Typical Properties                                      | Nominal Value | Units             | Test Method |
|---------------------------------------------------------|---------------|-------------------|-------------|
| <b>Physical</b>                                         |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)                        | 9.0           | g/10 min          | ISO 1133    |
| Density                                                 | 1.23          | g/cm <sup>3</sup> | ISO 1183    |
| <b>Mechanical</b>                                       |               |                   |             |
| Tensile Stress at Yield                                 | 32            | MPa               | ISO 527-2   |
| Flexural Modulus                                        | 4000          | MPa               | ISO 178     |
| <b>Impact</b>                                           |               |                   |             |
| Notched Izod Impact Strength, (23 °C, Type 1, Notch A)  | 5.0           | kJ/m <sup>2</sup> | ISO 180     |
| <b>Hardness</b>                                         |               |                   |             |
| Shore Hardness, (Shore D)                               | 63            |                   | ISO 868     |
| <b>Thermal</b>                                          |               |                   |             |
| Vicat Softening Temperature, (A (10N), 50 °C/h)         | 150           | °C                | ISO 306     |
| Deflection Temperature Under Load Unannealed (0.45 MPa) | 130           | °C                | ISO 75-2/B  |
| Deflection Temperature Under Load Unannealed (1.80 MPa) | 88            | °C                | ISO 75-2/A  |
| <b>Flammable</b>                                        |               |                   |             |
| Burning Rate                                            |               |                   |             |
| (2.00 mm)                                               | <100          | mm/min            | FMVSS 302   |
| (2.00 mm)                                               | <100          | mm/min            | ISO 3795    |
| <b>UL Information</b>                                   |               |                   |             |
| Flame Rating                                            | HB            |                   | UL 94       |



| Injection Parameters   | Nominal Value | Units |
|------------------------|---------------|-------|
| Drying Time            | 2.0 to 3.0    | hr    |
| Drying Temperature     | 80            | °C    |
| Processing (Melt) Temp | 220 to 260    | °C    |
| Mold Temperature       | 30 to 60      | °C    |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.