

Technical Data Sheet

Perlex R3533 RED7-0952



Polycarbonate

Product Description

30% glass fibre filled FR PC with added UV stabilisation matched to RAL 3020

Regulatory Status

For regulatory compliance information, see *Perlex R3533 RED7-0952* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Europe; Latin America; North America
Additive	Flame Retardant
Application	Machine/Mechanical Parts
Filler/Reinforcement	Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (300 °C/1.2 kg)	8.0	g/10 min	ISO 1133
Density	1.35	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break	2	%	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Tensile Stress at Break	95	MPa	ISO 527-2
Tensile Modulus	8750	MPa	ISO 527-1
Flexural Stress	143	MPa	ISO 178
Impact			
Notched Izod Impact (Area), (23 °C)	10.0	kJ/m ²	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (1.80 MPa)	135	°C	ISO 75-2/A
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	FMVSS 302
(2.00 mm)	<100	mm/min	ISO 3795
Glow Wire Ignition Temperature			
(3.0 mm)	850	°C	IEC 60695-2-13
(2.0 mm)	850	°C	IEC 60695-2-13
(1.0 mm)	850	°C	IEC 60695-2-13
UL Information			
Flame Rating			
(1.6 mm)	V-0		UL 94
(3.2 mm)	V-0		UL 94

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.