

Technical Data Sheet

Petrothene NA980000



Low Density Polyethylene

Product Description

Petrothene NA980000 is a low density homopolymer resin selected by customers for use in shrink packaging, bundling, pallet wrap and heavy-duty liner applications. NA980000 is also selected by customers for use in blow molding squeeze bottles and other specialty applications. Excellent bubble stability, melt strength, impact and shrinkage are key attributes of NA980000.

Regulatory Status

For regulatory compliance information, see *Petrothene* NA980000 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Agriculture Film; Bags & Pouches; Bottles and Vials; Bottles For Consumer Goods; Bottles for Industrial Use; Can Liners; Clear Containers; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Liner Film; Opaque Containers; Shrink Film; Specialty Film; Textile Packaging Film
Market	Flexible Packaging; Rigid Packaging
Processing Method	Blown Film; Extrusion Blow Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.25	g/10 min	0.25	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.920	g/cm ³	0.920	g/cm ³	ASTM D1505
Product Density, (23 °C)	0.920	g/cm ³	0.920	g/cm ³	ASTM D1505
Mechanical					
Tensile Strength at Break	2600	psi	17.9	MPa	ASTM D638
Tensile Strength at Yield	1420	psi	9.79	MPa	ASTM D638
Tensile Elongation at Break	700	%	700	%	ASTM D638
Tensile Elongation at Yield	100	%	100	%	ASTM D638
Film					
Dart Drop Impact Strength, F50	180	g	180	g	ASTM D1709
Tensile Strength at Break					
MD	3000	psi	20.7	MPa	ASTM D882
TD	2800	psi	19.3	MPa	ASTM D882
Tensile Elongation at Break					
MD	310	%	310	%	ASTM D882
TD	430	%	430	%	ASTM D882
1% Secant Modulus					
MD	30000	psi	207	MPa	ASTM D882
TD	35000	psi	241	MPa	ASTM D882
Hardness					
Shore Hardness, (Shore D)	45		45		ASTM D2240
Thermal					

Vicat Softening Temperature	199 °F	93 °C	ASTM D1525
Low Temperature Brittleness, F ₅₀	-103 °F	-75 °C	ASTM D746
Additive			
Slip	None	None	LYB Method
Antiblock	None	None	LYB Method

Product	Product Density(g/cm ³)	Antiblock (ppm)
NA980000	0.920	None
NA983085	0.922	4000

Notes

Data obtained from 1.25 mil (32 micron) film produced on a blown film line with a 8" (203 mm) die, 350°F (177°C) melt temperature, 2:1 BUR, 0.025" die gap at 150 lbs/hr.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.