

PLASTRON™ PA66-GF50-02

Polyamide 66
Daicel Polymer Ltd.

Technical Data

General		
Material Status	• Commercial: Active	
Search for UL Yellow Card	• Daicel Polymer Ltd. • PLASTRON™	
Availability	• Asia Pacific	
Filler / Reinforcement	• Long Glass Fiber, 50% Filler by Weight	
Forms	• Pellets	
Physical	Nominal Value Unit	Test Method
Density	1.56 g/cm³	ISO 1183
Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	17000 MPa	ISO 527-2
Tensile Stress (Yield)	270 MPa	ISO 527-2
Tensile Strain (Break)	2.3 %	ISO 527-2
Flexural Modulus	16300 MPa	ISO 178
Flexural Strength	400 MPa	ISO 178
Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength	47 kJ/m²	ISO 179/1eA
Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature 1.8 MPa, Unannealed	261 °C	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.