

Technical Data Sheet

Polyaxis PD 3000-01G NATURAL



Polypropylene Copolymer

Product Description

Polyaxis PD 3000 is a polypropylene specifically designed for rotational molding. A long term UV package and robust antioxidant system allow this material to be used in a variety of applications.

Regulatory Status

For regulatory compliance information, see *Polyaxis* PD 3000-01G NATURAL [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Rotomolding
Forms	Pellets; Powder
Appearance	Black; Natural Color
Additive	Long Term UV-15 Stabilizer
Application	Automotive Under the Hood; Bottles; Containers; High Temperature Applications

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density - Specific Gravity	0.9	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (51 mm/min, Rotational Molded)	25.9	MPa	ASTM D638
Environmental Stress Crack Resistance, (Compression Molded, F50, 100% Igepal)	>1000	hr	ASTM D1693
Flexural Modulus, (Rotational Molded, 1% Secant)	1290	MPa	ASTM D790
Tensile Elongation at Break, (51 mm/min, Rotational Molded)	40	%	ASTM D638
Impact			
Impact Strength			
(23 °C, 6.35 mm, Rotational Molded)	27	J	ARM
(23 °C, 3.18 mm, Rotational Molded)	20	J	ARM
Thermal			
Deflection Temperature Under Load Unannealed (264 psi), (3.18 mm, Rotational Molded)	49.9	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi), (Rotational Molded)	105	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.