

Technical Data Sheet

Polyflam 34N3001NY1006YEW



Polybutylene Terephthalate

Product Description


Unreinforced Flame Retardant PBT

Regulatory Status

For regulatory compliance information, see 34N3001NY1006YEW [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Pending Approval
Availability	North America
Forms	Pellets
Additive	Flame Retardant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (250 °C/2.16 kg)	10	g/10 min	ASTM D1238
Density - Specific Gravity	1.35	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	53.1	MPa	ASTM D638
Flexural Modulus, (Tangent)	2240	MPa	ASTM D790
Impact			
Gardner Impact	36.2	J	ASTM D3029
Notched Izod Impact	32	J/m	ASTM D256
UL Information			
Flame Rating			
(1.5 mm)	V-0		UL 94
(3.0 mm)	V-0		UL 94



Injection Parameters	Nominal Value	Units
Drying Time, (Desiccant Dryer)	2.0 to 4.0	hr
Drying Temperature, (Desiccant Dryer)	121	°C
Suggested Max Moisture	<0.020	%
Nozzle Temperature	238 to 266	°C
Screw Speed	50 to 80	rpm
Processing (Melt) Temp	238 to 266	°C
Front Temperature	238 to 266	°C
Middle Temperature	238 to 254	°C
Rear Temperature	238 to 249	°C
Injection Rate	Moderate	
Back Pressure	<0.689	MPa
Mold Temperature	66 to 88	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.