

Technical Data Sheet

Polyflam RPP 4220 MD 16V0 ORE16835



Polypropylene, Homopolymer

Product Description

20% glass fibre reinforced flame retardant polypropylene homopolymer compound free of halogens


Regulatory Status

For regulatory compliance information, see *Polyflam RPP 4220 MD 16V0 ORE16835* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific; Europe
Processing Method	Injection Molding
Attribute	Halogen Free; Homopolymer
Additive	Flame Retardant
Filler/Reinforcement	Glass Fiber, 20%
Resin ID	PP GF20 FR(51)

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (230 °C/2.16 kg)	5.0	cm ³ /10 min	ISO 1133
Density, (Method A)	1.21	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break, (Type 1A, 5 mm/min)	3.0	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 5 mm/min)	72.0	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	6400	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	35	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A (10N))	165	°C	ISO 306
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	158	°C	ISO 75-2/B
(1.80 MPa, Unannealed)	138	°C	ISO 75A-1, -2
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600	V	UL 746A
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Glow Wire Flammability Index			
(1.5 mm) - Conditioned	960	°C	IEC 60695-2-12
(3.0 mm) - Conditioned	960	°C	IEC 60695-2-12

Glow Wire Ignition Temperature			
(1.5 mm, Passes)	800	°C	IEC 60695-2-13
(3.0 mm, Passes)	800	°C	IEC 60695-2-13
UL Information			
Flammability Classification			
(1.6 mm)	V-0		IEC 60695-11-10, -20
(3.2 mm)	V-0		IEC 60695-11-10, -20



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	70 to 80	°C
Nozzle Temperature	220	°C
Processing (Melt) Temp	200 to 230	°C
Front Temperature	210	°C
Holding Pressure	40.0 to 90.0	MPa
Middle Temperature	200	°C
Rear Temperature	180	°C
Injection Rate	Slow-Moderate	
Back Pressure	5.00 to 10.0	MPa
Mold Temperature	40 to 80	°C
Injection Pressure	80.0 to 120	MPa
Cushion	<5.00	mm

Notes

These are typical property values not to be construed as specification limits.

Processing notes

Melt contacting surfaces should be made of a high quality, corrosive resistant steel. Positive experiences have been made with steel qualities containing > 12% chromium.

Avoid processing at very barrel high temperatures or above the recommended melt temperature range as this can increase risk of deposit onto the tool surfaces. Avoid long residence times. At start and end of production, it is recommended to purge clean with non-flame retardant polymer or a polyolefin.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.