

Technical Data Sheet

Polyfort FPP 1182E-31 BLACK



Polypropylene, Unspecified (PP, Unspecified)

Product Description


20% Talc Filled Polypropylene, extrusion grade. Mainly used in profile extrusion

Regulatory Status

For regulatory compliance information, see Polyfort FPP 1182E-31 BLACK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Extrusion; Injection Molding
Filler/Reinforcement	Talc, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.05	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (50 mm/min)	31.0	MPa	ASTM D638
Flexural Modulus, (1.3 mm/min)	2600	MPa	ASTM D790
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	62	°C	ASTM D648
Additional Information			
Filler Content	20	%	ASTM D5630



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C

Processing (Melt) Temp	220 to 260 °C
Injection Rate	Moderate- Fast
Mold Temperature	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.