

Polyfort FPP 20 GB

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

Product Description

20% glass bead reinforced PP-Homopolymer with high stiffness and dimension stability

General

Filler / Reinforcement	• Glass Bead, 20% Filler by Weight
Processing Method	• Injection Molding


Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm ³	1.04 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	10 cm ³ /10min	10 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	247000 psi	1700 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	3480 psi	24.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	8.0 %	8.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	0.95 ft·lb/in ²	2.0 kJ/m ²	
73°F (23°C)	1.9 ft·lb/in ²	4.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	7.1 ft·lb/in ²	15 kJ/m ²	
73°F (23°C)	17 ft·lb/in ²	35 kJ/m ²	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	10600 psi	73.0 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	246 °F	119 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	178 °F	81.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	185 °F	85.0 °C	ISO 306/B50
--	302 °F	150 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Polyfort FPP 20 GB

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.
Ensure good mold venting
Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.