

Polyfort FPP 20 T K2037 NATUR

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

Product Description

20% talc filled PP-Homopolymer

General

Filler / Reinforcement	• Talc, 20% Filler by Weight
Features	• Food Contact Acceptable • Homopolymer
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PP-M<

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm ³	1.04 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	8.0 cm ³ /10min	8.0 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	355000 psi	2450 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	4640 psi	32.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	5.0 %	5.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	0.71 ft·lb/in ²	1.5 kJ/m ²	
73°F (23°C)	1.4 ft·lb/in ²	3.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	8.6 ft·lb/in ²	18 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	243 °F	117 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	172 °F	78.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	205 °F	96.0 °C	ISO 306/B50
--	309 °F	154 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	IEC 60093
Volume Resistivity	1.0E+13 ohms·m	1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	1.1 in/min	27 mm/min	ISO 3795
0.0787 In (2.00 Mm)	1.1 in/min	27 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1290 °F	700 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F	725 °C	
0.12 In (3.0 Mm)	1340 °F	725 °C	

***Polyfort* FPP 20 T K2037 NATUR**


Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Polyfort FPP 20 T K2037 NATUR

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.
Ensure good mold venting
Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.