

Technical Data Sheet

Polyfort PP6A0ULWT79



Polypropylene Copolymer

Product Description


PP6A0BK21 is a High-Impact Polypropylene

Regulatory Status

For regulatory compliance information, see PP6A0ULWT79 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Injection Molding
Attribute	High Impact Resistance
Forms	Pellets
Appearance	Colors Available

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7.9	g/10 min	ASTM D1238
Density - Specific Gravity	0.908	g/cm ³	ASTM D792
Mechanical			
Tensile Elongation at Yield	16	%	ASTM D638
Tensile Strength at Yield, (23 °C)	17.9	MPa	ASTM D638
Flexural Modulus	839	MPa	ASTM D790
Impact			
Gardner Impact	22.6	J	ASTM D5420
Notched Izod Impact, (23 °C, 3.18 mm)	710	J/m	ASTM D256
Thermal			
RTI Elec, (1.5 mm)	65.0	°C	UL 746B
RTI Imp, (65.0 mm)	65.0	°C	UL 746B
RTI Str	65	°C	UL 746B
UL Information			
Flame Rating, (1.5 mm) (UL 94)	HB		



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Processing (Melt) Temp	193 to 232	°C
Front Temperature	177 to 232	°C
Middle Temperature	177 to 232	°C
Rear Temperature	177 to 232	°C
Injection Rate	Moderate	
Back Pressure	0.138 to 2.07	MPa
Mold Temperature	21 to 49	°C
Cushion	6.35 to 12.7	mm

Notes

These are typical property values not to be construed as specification limits. The typical values for this product may have been tested on a natural grade.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.