

## Technical Data Sheet

### Polyfort TPP40AE05UL-BKBLK



Polypropylene, Homopolymer

#### Product Description

Polyfort TPP40AE05UL-BKBLK is a Polypropylene Homopolymer Talc, 42% filled material and is typically used in Injection Molding applications. Features include: Heat Stabilized, and Homopolymer.

#### Regulatory Status

For regulatory compliance information, see TPP40AE05UL-BKBLK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

|                             |                              |
|-----------------------------|------------------------------|
| <b>Status</b>               | Commercial: Active           |
| <b>Availability</b>         | Latin America; North America |
| <b>Processing Method</b>    | Injection Molding            |
| <b>Attribute</b>            | Heat Stabilized; Homopolymer |
| <b>Forms</b>                | Pellets                      |
| <b>Appearance</b>           | Black                        |
| <b>Additive</b>             | Heat Stabilizer              |
| <b>Filler/Reinforcement</b> | Talc, 42%                    |

| Typical Properties                                     | Nominal Value | Units             | Test Method |
|--------------------------------------------------------|---------------|-------------------|-------------|
| <b>Physical</b>                                        |               |                   |             |
| Melt Flow Rate, (230 °C/2.16 kg)                       | 5.5           | g/10 min          | ASTM D1238  |
| Density - Specific Gravity                             | 1.27          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                                      |               |                   |             |
| Tensile Strength, (23 °C)                              | 30.3          | MPa               | ASTM D638   |
| Flexural Modulus                                       |               |                   |             |
| (23 °C, 1% Secant)                                     | 2990          | MPa               | ASTM D790   |
| (23 °C, Tangent)                                       | 3830          | MPa               | ASTM D790   |
| Tensile Elongation at Break, (23 °C)                   | 6.0           | %                 | ASTM D638   |
| Flexural Strength, (23 °C)                             | 51.0          | MPa               | ASTM D790   |
| <b>Impact</b>                                          |               |                   |             |
| Gardner Impact, (23 °C)                                | 0.565         | J                 | ASTM D5420  |
| Unnotched Izod Impact, (23 °C)                         | 220           | J/m               | ASTM D4812  |
| Notched Izod Impact, (23 °C)                           | 21            | J/m               | ASTM D256   |
| <b>Hardness</b>                                        |               |                   |             |
| Durometer Hardness, (Shore D)                          | 75            |                   | ASTM D2240  |
| <b>Thermal</b>                                         |               |                   |             |
| Deflection Temperature Under Load Unannealed (264 psi) | 82.2          | °C                | ASTM D648   |
| Deflection Temperature Under Load Unannealed (66 psi)  | 132           | °C                | ASTM D648   |



| Injection Parameters    | Nominal Value  | Units              |
|-------------------------|----------------|--------------------|
| Drying Time             | 2.0 to 3.0     | hr                 |
| Drying Temperature      | 80             | °C                 |
| Clamp Tonnage           | 2.8 to 4.1     | kN/cm <sup>2</sup> |
| Nozzle Temperature      | 216 to 218     | °C                 |
| Screw Speed             | 100 to 150     | rpm                |
| Processing (Melt) Temp  | 220 to 260     | °C                 |
| Front Temperature       | 213 to 216     | °C                 |
| Screw L/D Ratio         | 20.0-1.0       |                    |
| Screw Compression Ratio | 2.0-1.0        |                    |
| Middle Temperature      | 210 to 213     | °C                 |
| Rear Temperature        | 204 to 210     | °C                 |
| Back Pressure           | 0.138 to 0.345 | MPa                |
| Mold Temperature        | 30 to 60       | °C                 |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.