

## Technical Data Sheet

### *Polyfort* TPP1C30HBNANAT



Polypropylene, Homopolymer

#### Product Description

*Polyfort* TPP1C30HBNANAT is a Polypropylene Homopolymer Talc, 30% filled material and is typically used in Injection Molding applications. Features include: Homopolymer.

#### Regulatory Status

For regulatory compliance information, see TPP1C30HBNANAT [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

|                      |                   |
|----------------------|-------------------|
| Status               | Discontinued      |
| Availability         | North America     |
| Processing Method    | Injection Molding |
| Attribute            | Homopolymer       |
| Forms                | Pellets           |
| Filler/Reinforcement | Talc, 30%         |

| Typical Properties                                     | Nominal Value | Units             | Test Method |
|--------------------------------------------------------|---------------|-------------------|-------------|
| <b>Physical</b>                                        |               |                   |             |
| Melt Flow Rate                                         | 16            | g/10 min          | ASTM D1238  |
| Density - Specific Gravity                             | 1.14          | g/cm <sup>3</sup> | ASTM D792   |
| <b>Mechanical</b>                                      |               |                   |             |
| Tensile Strength at Yield, (23 °C)                     | 31.7          | MPa               | ASTM D638   |
| Flexural Modulus, (23 °C, Tangent)                     | 2830          | MPa               | ASTM D790   |
| <b>Impact</b>                                          |               |                   |             |
| Gardner Impact                                         | 0.452         | J                 | ASTM D3029  |
| Notched Izod Impact, (23 °C, 3.18 mm)                  | 21            | J/m               | ASTM D256   |
| <b>Hardness</b>                                        |               |                   |             |
| Durometer Hardness, (Shore D)                          | 75            |                   | ASTM D2240  |
| <b>Thermal</b>                                         |               |                   |             |
| Deflection Temperature Under Load Unannealed (264 psi) | 71.1          | °C                | ASTM D648   |
| Deflection Temperature Under Load Unannealed (66 psi)  | 121           | °C                | ASTM D648   |



| Injection Parameters   | Nominal Value | Units |
|------------------------|---------------|-------|
| Drying Time            | 2.0 to 4.0    | hr    |
| Drying Temperature     | 82 to 104     | °C    |
| Processing (Melt) Temp | 199 to 227    | °C    |
| Front Temperature      | 177 to 221    | °C    |
| Middle Temperature     | 177 to 221    | °C    |
| Rear Temperature       | 177 to 221    | °C    |
| Injection Rate         | Moderate      |       |
| Back Pressure          | 0.138 to 2.07 | MPa   |
| Mold Temperature       | 21 to 49      | °C    |
| Cushion                | 6.35 to 12.7  | mm    |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.