

Technical Data Sheet

Polyfort TPP2B20HSUVBK55BLK



Polypropylene, Homopolymer

Product Description


TPP2B20HSUVBK55 is a 20% Talc-Filled, Heat and UV Stabilized Polypropylene Homopolymer

Regulatory Status

For regulatory compliance information, see TPP2B20HSUVBK55BLK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Processing Method	Injection Molding
Attribute	Heat Stabilized; UV Stabilized
Forms	Pellets
Appearance	Black
Filler/Reinforcement	Talc, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ASTM D1238
Density	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield	32	MPa	ISO 527-2
Flexural Modulus, (Chord)	2040	MPa	ISO 178
Impact			
Notched Izod Impact Strength	4.7	kJ/m ²	ISO 180



Injection Parameters

LyondellBasell
Technical Data Sheet
Date: 12/11/2024

Injection Parameters	Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Processing (Melt) Temp	199 to 227	°C
Front Temperature	177 to 221	°C
Middle Temperature	177 to 221	°C
Rear Temperature	177 to 221	°C
Injection Rate	Moderate	
Back Pressure	0.138 to 2.07	MPa
Mold Temperature	21 to 49	°C
Cushion	6.35 to 12.7	mm

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.