

## Technical Data Sheet

### *Polyman* ABS M/TK K1516 BUE 45165



Acrylonitrile Butadiene Styrene

#### Product Description

ABS standard grade with higher softening temperature

#### Regulatory Status

For regulatory compliance information, see *Polyman* ABS M/TK K1516 BUE 45165 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

|                          |                                                         |
|--------------------------|---------------------------------------------------------|
| <b>Status</b>            | Commercial: Active                                      |
| <b>Availability</b>      | Africa-Middle East; Asia-Pacific; Europe; Latin America |
| <b>Processing Method</b> | Injection Molding                                       |
| <b>Resin ID</b>          | ABS                                                     |

| Typical Properties                                                  | Nominal Value | Units                   | Test Method   |
|---------------------------------------------------------------------|---------------|-------------------------|---------------|
| <b>Physical</b>                                                     |               |                         |               |
| Melt Volume Flow Rate, (220 °C/10.0 kg)                             | 23            | cm <sup>3</sup> /10 min | ISO 1133      |
| Density, (Method A)                                                 | 1.05          | g/cm <sup>3</sup>       | ISO 1183      |
| <b>Mechanical</b>                                                   |               |                         |               |
| Tensile Stress at Yield, (Type 1A, 50 mm/min)                       | 52.0          | MPa                     | ISO 527-2     |
| Tensile Strain at Yield, (Type 1A, 50 mm/min)                       | 2.5           | %                       | ISO 527-2     |
| Tensile Modulus, (1 mm/min, Type 1A)                                | 2500          | MPa                     | ISO 527-1     |
| <b>Impact</b>                                                       |               |                         |               |
| Charpy Impact Strength - Notched                                    |               |                         |               |
| (23 °C, Type 1, Edgewise, Notch A)                                  | 15            | kJ/m <sup>2</sup>       | ISO 179       |
| (-30 °C, Type 1, Edgewise, Notch A)                                 | 7.0           | kJ/m <sup>2</sup>       | ISO 179       |
| Charpy Impact Strength - Unnotched                                  |               |                         |               |
| (23 °C, Type 1, Edgewise)                                           | No Break      |                         | ISO 179       |
| (-30 °C, Type 1, Edgewise)                                          | 80            | kJ/m <sup>2</sup>       | ISO 179       |
| <b>Hardness</b>                                                     |               |                         |               |
| Ball Indentation Hardness, (H 358/30)                               | 105           | MPa                     | ISO 2039-1    |
| <b>Thermal</b>                                                      |               |                         |               |
| Vicat Softening Temperature, (B (50N), 50 °C/h)                     | 98.0          | °C                      | ISO 306       |
| Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise) | 96.0          | °C                      | ISO 75-2/B    |
| Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise) | 92.0          | °C                      | ISO 75-2/A    |
| <b>Electrical</b>                                                   |               |                         |               |
| Volume Resistivity                                                  | >1.0E+13      | ohm*m                   | IEC 62631-3-1 |
| Surface Resistivity                                                 | >1.0E+15      | ohm                     | IEC 60093     |
| <b>Flammable</b>                                                    |               |                         |               |
| Burning Rate                                                        |               |                         |               |
| (2.00 mm)                                                           | <100          | mm/min                  | FMVSS 302     |
| (2.00 mm)                                                           | <100          | mm/min                  | ISO 3795      |

|                              |        |                      |
|------------------------------|--------|----------------------|
| Glow Wire Flammability Index |        |                      |
| (1.5 mm)                     | 650 °C | IEC 60695-2-12       |
| (3.0 mm)                     | 650 °C | IEC 60695-2-12       |
| <b>UL Information</b>        |        |                      |
| Flammability Classification  |        |                      |
| (1.5 mm)                     | HB     | IEC 60695-11-10, -20 |
| (3.0 mm)                     | HB     | IEC 60695-11-10, -20 |
| UL File Number               | E86615 |                      |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.