

Technical Data Sheet

Polyvin PVC 4507-31 00 BLACK



Polyvinyl Chloride, Unspecified

Product Description


Flexible PVC formulation for general purpose molding applications requiring good dry touch, excellent weathering and ease of processing.

Regulatory Status

For regulatory compliance information, see Polyvin PVC 4507-31 00 BLACK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Pending Approval
Availability	North America
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.21	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (510 mm/min, Type IV)	4.83	MPa	ASTM D638
Tensile Elongation at Break, (510 mm/min, Type IV)	350	%	ASTM D638
Tear Strength, (51 mm/min)	25.4	kN/m	ASTM D624
Hardness			
Durometer Hardness, (Shore A)	56		ASTM D2240



Injection Parameters	Nominal Value	Units
Nozzle Temperature	177	°C
Processing (Melt) Temp	177	°C
Front Temperature	179	°C
Middle Temperature	179	°C

Rear Temperature	174 °C
Mold Temperature	27 to 38 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.