

Santoprene™ 121-80B200

Thermoplastic Vulcanizate

Product Description

A soft, black, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is specially formulated to enhance bonding onto EPDM vulcanized parts and TPV materials. It offers better adhesion on a small contact area, such as for weatherseals with thin lips or complex geometry. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Adheres to TPV and vulcanized EPDM rubber over a wide range of temperatures.
- High flexibility and targeted to automotive profiles, TPV or EPDM rubber.
- Higher gloss enables matching better extruded profile mating surface.
- Used in sealing applications.
- Corner Molding.

General

Applications	▪ Automotive - Weather Seals	
Uses	▪ Corner Molding	▪ Outdoor Applications
RoHS Compliance	▪ RoHS Compliant	
Color	▪ Black	
Form(s)	▪ Pellets	
Processing Method	▪ Injection Molding	▪ Multi Injection Molding

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.910	0.910	ASTM D792
Density	0.910 g/cm ³	0.910 g/cm ³	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C)	81	81	

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	566 psi	3.90 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	566 psi	3.90 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	1730 psi	11.9 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	1730 psi	11.9 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	730 %	730 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	730 %	730 %	ISO 37

Injection Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

Additional Information

Where applicable, test results based on fan gated, injection molded plaques.

Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.

All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

Santoprene™ 121-80B200

Thermoplastic Vulcanizate

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Safety Data Sheet, Injection Molding Guide and Technical Literature (TL) on "Injection Molding of Corners and End Caps to EPDM Weatherseals".

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.