

Santoprene™ 123-50S200

Thermoplastic Vulcanizate

Product Description

A hard, black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material has low friction and is especially designed for use as a co-extruded slip-coat layer on weatherseal applications. It can be used as an alternative to spray-on slip-coat systems used in automotive weatherseal applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for extrusion. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Designed for applications requiring excellent wear resistance, excellent weather resistance or part surface with low friction factor.
- Co-extrudable with other olefin thermoplastic rubbers.
- Designed for excellent surface smoothness and flexibility as slip-coating material.

General

Uses	▪ Outdoor Applications
Color	▪ Black
Form(s)	▪ Pellets
Processing Method	▪ Coextrusion

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.950	0.950	ASTM D792
Density	0.950 g/cm ³	0.950 g/cm ³	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore D, 15 sec, 73°F (23°C)	50	50	

Extrusion Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and die design, please consult our Extrusion Molding Guide.

Additional Information

Where applicable, test results based on fan gated, injection molded plaques.

All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Desiccant drying for 4 hours at 65°C (150°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Safety Data Sheet and Extrusion Guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.