

RESILIENCE® PP5113 B44

GEON Performance Solutions - Polypropylene Homopolymer

Monday, June 17, 2024

General Information

Product Description

The GEON® family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Talc, 13% Filler by Weight		
Features	• General Purpose		
Uses	• Automotive Applications • Construction Applications	• Consumer Applications • General Purpose	• Industrial Applications
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.00 g/cm ³	1.00 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19 g/10 min	19 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	4790 psi	33.0 MPa	ISO 527-2
Flexural Modulus	334000 psi	2300 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength (73°F (23°C))	1.4 ft·lb/in ²	3.0 kJ/m ²	ISO 180
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate	< 3.9 in/min	< 100 mm/min	ISO 3795

Notes

¹ Typical properties: these are not to be construed as specifications.