

Technical Data Sheet

Ronfalin A 30U ANTHRACITE GRY6-2421



Acrylonitrile Butadiene Styrene

Product Description

General Purpose, UV stabilized ABS

Regulatory Status

For regulatory compliance information, see *Ronfalin A 30U ANTHRACITE GRY6-2421* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Limited Issue
Availability	Africa-Middle East; Asia-Pacific; Europe; North America
Processing Method	Injection Molding
Attribute	UV Stabilized
Resin ID	ABS

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/10.0 kg)	29	g/10 min	ISO 1133
Density, (Method A)	1.04	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield	37	MPa	ISO 527-2
Tensile Strain at Break	15	%	ISO 527-2
Flexural Modulus	2170	MPa	ISO 178
Tensile Modulus, (1 mm/min, Type 1A)	2050	MPa	ISO 527-1
Impact			
Unnotched Izod Impact Strength, (23 °C)	15	kJ/m ²	ISO 180
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	93.0	°C	ISO 306
Flammable			
Glow Wire Flammability Index	650	°C	IEC 60695-2-12
Glow Wire Ignition Temperature	700	°C	IEC 60695-2-13
UL Information			
Flame Rating, (3.2 mm)	HB		UL 94



Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	230 to 250	°C
Mold Temperature	40 to 80	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.