

Technical Data Sheet

Ronfalin N25 GRY6-2716



Acrylonitrile Butadiene Styrene + PA

Product Description

PA6/ABS alloy with very high impact strength with excellent flow to enable reproducibility of the mould tool surface.

Regulatory Status

For regulatory compliance information, see *Ronfalin N25 GRY6-2716* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status Limited Issue

Availability Africa-Middle East; Asia-Pacific; Europe; Latin America; North America

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate			
(240 °C/10.0 kg)	30	g/10 min	ISO 1133
(240 °C/5.0 kg)	10	g/10 min	ISO 1133
Density	1.07	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield	42	MPa	ISO 527-2
Tensile Strain at Break	>50	%	ISO 527-2
Flexural Modulus	1700	MPa	ISO 178
Tensile Stress at Break	36	MPa	ISO 527-2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	60	kJ/m ²	ISO 179
(-20 °C)	15	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179
Thermal			
Vicat Softening Temperature, (B (50N), 120 °C/h)	106	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	92	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	70	°C	ISO 75-2/A
Electrical			
Dielectric Strength	40	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI), (Solution A)	>600	V	IEC 60112

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.