

Technical Data Sheet

Ronfalin SAN 4701 GF35 NAT



Styrene Acrylonitrile

Product Description


35% glass fiber reinforced, High Heat resistant SAN compound

Regulatory Status

For regulatory compliance information, see *Ronfalin* SAN 4701 GF35 NAT [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Europe; Latin America
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; High Strength
Filler/Reinforcement	Glass Fiber, 35%
Resin ID	SAN-GF

Typical Properties	Nominal Value	Units	Test Method
Mechanical			
Tensile Strain at Break, (Type 1A, 5 mm/min)	1.0	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 5 mm/min)	96.0	MPa	ISO 527-2
Impact			
Charpy Impact Strength - Notched, (-30 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (-30 °C, Type 1, Edgewise)	9.0	kJ/m ²	ISO 179
Hardness			
Ball Indentation Hardness, (H 358/30)	77.0	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	120	°C	ISO 306



Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.