

OnFlex™ S KA 40A-3S1767

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™-S KA thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds are specially compatibilized to provide excellent adhesion to polyamide polymers including PA6, PA6.6, PA11 and PA12. OnFlex™-S KA can be processed by 2K molding or overmolding, insert molding or co-extrusion. In addition to this, OnFlex™-S KA compounds are formulated to provide excellent compression set performance, even at elevated temperatures, a wide hardness range, good colourability and surface appearance, good mechanical properties and excellent UV resistance.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Adhesion	• High Heat Resistance	• UV Resistant
Uses	• Automotive Applications • Consumer Applications	• Industrial Applications • Overmolding	• Power/Other Tools
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Coextrusion	• Multi Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.09 g/cm ³	1.09 g/cm ³	ISO 1183
Molding Shrinkage ²			Internal Method
Across Flow : 72 hr, 0.0787 in (2.00 mm)	0.90 %	0.90 %	
Flow : 72 hr, 0.0787 in (2.00 mm)	2.9 %	2.9 %	
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress (100% Strain)	145 psi	1.00 MPa	ISO 37
Tensile Stress (300% Strain)	334 psi	2.30 MPa	ISO 37
Tensile Stress (Break)	435 psi	3.00 MPa	ISO 37
Tensile Elongation (Break)	410 %	410 %	ISO 37
Tear Strength	99.4 lbf/in	17.4 kN/m	ISO 34-1
Compression Set			ISO 815
73°F (23°C), 72 hr	13 %	13 %	
158°F (70°C), 22 hr	29 %	29 %	
212°F (100°C), 22 hr	57 %	57 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A, 10 sec)	40	40	ISO 48-4
Additional Information	Typical Value (English)	Typical Value (SI)	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	Styrenic Thermoplastic Elastomer (TES)	
Properties are measured using injection molded plaques.			

Copyright © 2022 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	392 to 500 °F	200 to 260 °C
Mold Temperature	86 to 122 °F	30 to 50 °C
Injection Rate	Moderate	Moderate

Notes

¹ Typical values are not to be construed as specifications.

² Measured on 100x100x2mm plates, results may vary depending on processing parameters, part geometry and tool design.