

Technical Data Sheet

Sequel 2396 SP NH-900L BLACK



Polypropylene Compounds

Product Description

Sequel 2396 SP NH-900L BLACK is a mineral filled, scratch-resistant thermoplastic polyolefin (TPO) material. It is typically used for molded-in-color automotive interior applications that require stiffness, dimensional stability, and high impact characteristics.

Regulatory Status

For regulatory compliance information, see *Sequel* 2396 SP NH-900L BLACK [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Instrument Panels; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good Processability; Good Stiffness; High Impact Resistance; Pleasing Surface Appearance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ASTM D1238
Density, (23 °C)	1.00	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus, (23 °C) 30 mm/min test speed	2700	MPa	ASTM D790
Tensile Stress at Yield, (23 °C) 30 mm/min test speed	25	MPa	ASTM D638
Impact			
Notched Izod Impact Strength (23 °C)	450	J/m	ASTM D256
(-30 °C)	45	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	133	°C	ASTM D648
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			