

SLOVAMID® 66 GF 40 E/2M

Polyamide 66

Plastcom



IDES | Prospector

ides.com/prospector

Technical Data

Product Description

PA 66 for extrusion and injection moulding grade. Chemically reinforced with 40% glass fibre, determined for extrusion of profile systems for window profiles. Delivered in black color.

General

Material Status	• Commercial: Active	
Search for UL Yellow Card	• Plastcom	
Availability	• Europe	
Filler / Reinforcement	• Glass Fiber Reinforcement, 40% Filler by Weight	
Additive	• Heat Stabilizer	
Features	• Chemically Coupled	• Heat Stabilized
Uses	• Automotive Applications • Electrical/Electronic Applications	• Engineering Parts • Gears
Appearance	• Black	
Processing Method	• Extrusion	
Resin ID (ISO 1043)	• PA 66	

Physical	Nominal Value Unit	Test Method
Density	1.43 g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	5.0 g/10 min	ISO 1133
Water Content	0.15 %	ISO 960

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	12300 MPa	ISO 527-2
Tensile Stress (Yield)	175 MPa	ISO 527-2
Tensile Strain (Yield)	3.5 %	ISO 527-2
Flexural Modulus	6500 MPa	ISO 178
Flexural Strength	230 MPa	ISO 178

Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength		ISO 179
-20°C	8.0 kJ/m²	
23°C	11 kJ/m²	
Charpy Unnotched Impact Strength		ISO 179
-20°C	75 kJ/m²	
23°C	75 kJ/m²	

Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature 0.45 MPa, Unannealed	250 °C	ISO 75-2/B
Vicat Softening Temperature	250 °C	ISO 306/B
Melting Temperature (DSC)	260 °C	ISO 3146

Electrical	Nominal Value Unit	Test Method
Surface Resistivity	1.0E+14 ohm	IEC 60093
Volume Resistivity	1.0E+15 ohm·cm	IEC 60093
Electric Strength	25 kV/mm	IEC 60243-1

Flammability	Nominal Value Unit	Test Method
Flame Rating	HB	UL 94
Glow Wire Ignition Temperature	650 °C	IEC 60695-2-13

Injection	Nominal Value Unit
Drying Temperature	80.0 °C
Drying Time	4.0 hr

SLOVAMID® 66 GF 40 E/2M

Polyamide 66

Plastcom

Injection	Nominal Value Unit
Processing (Melt) Temp	250 to 270 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

SLOVAMID® 66 GF 40 E/2M

Polyamide 66

Plastcom

Where to Buy

Supplier

Plastcom

Bratislava, Slovakia

Telephone: 00421 2 44 259 160

Web: <http://www.plastcom.sk/>

Distributor

Please contact the supplier to find a distributor for SLOVAMID® 66 GF 40 E/2M



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



Prospector Plastics Database - www.ides.com/prospector

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

– Birgit Elvardt Bader, Production Manager, Micotron

Power Searches

Property Search – select plastics by 500 key properties and design parameters.

Alternative Resins Search – find replacement plastics within minutes.

Automotive Plastics Search – easily locate automotive approved plastics.

Curve Data – view, overlay and export curve data.



Material Data Management – www.ides.com/datasheets

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

– Kevin Chase, Owner & President, Chase Plastics



Advertising – www.ides.com/advertise

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.

For more information, call: 800.788.4668 or 307.742.9227 ext. 220