

Technical Data Sheet

Softell TKG 259N NATRL



Polypropylene Compounds

Product Description

Softell TKG 259N NATRL is a glass fiber reinforced PP copolymer with superior dimensional stability, high stiffness, good surface appearance, and excellent scratch resistance. Product is available as natural pellet form.

Regulatory Status

For regulatory compliance information, see *Softell* TKG 259N NATRL [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good Surface Finish; Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ASTM D1238
Density, (23 °C)	1.01	kg/m ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	2100	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	36	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	36	kJ/m ²	ISO 180
(-30 °C)	10	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	135	°C	ISO 75B-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			