

TECAPAI® CM XP730 black - Stock Shapes

Chemical Designation

PAI (Polyamide-imide)

Colour

black

Density

1.47 g/cm³

Fillers

carbon fibres

production process: compression moulding

Main features

- very good thermal stability
- excellent dimensional stability
- excellent chemical resistance

Target Industries

- aircraft and aerospace technology
- process engineering
- chemical and refinery industry
- oil and gas industry

Mechanical properties	condition	value	test method	comment
Modulus of elasticity (tensile test)		1,200,000 psi	ASTM D 638	
Tensile strength at break		24,000 psi	ASTM D 638	
Elongation at break		4.0 %	ASTM D 638	
Flexural strength		37,000 psi	ASTM D 790	
Modulus of elasticity (flexural test)		1,300,000 psi	ASTM D 790	
Compression strength	1% strain	6,500 psi	ASTM D 695	
Compression strength	10% strain	40,000 psi	ASTM D 695	
Compression modulus		700,000 psi	ASTM D 695	
Impact strength (Izod)	notched	1.1 ft-lbs/in	ASTM D 256	
Shore hardness	D scale	94	ASTM D 2240	
Coefficient of friction	static	0.15	ASTM D 1894	
Coefficient of friction	dynamic	0.13	ASTM D 1894	
Thermal properties	condition	value	test method	comment
Glass transition temperature		529 °F	ASTM D3418	
Deflection temperature	@ 264 psi	526 °F	ASTM D 648	
Thermal expansion (CLTE)	range -40 °F to 302 °F	1.62 *10 ⁻⁵ in/in/°F	ASTM E 831	
Other properties	condition	value	test method	comment
Limiting PV		13,000 psi-fpm	ASTM D 3702	1)
Moisture absorption	saturation	1.4 %	ASTM D 570	(1) Calculated using a factor of safety of 4 with a testing speed of 100 fpm
Moisture absorption	24 hr immersion	0.2 %	ASTM D 570	
Flammability (UL94)	3.2 mm	V-0	-	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at