

TECHNYL®

TECHNYL® A 21T3 V25 BLACK 15N

TECHNICAL DATA SHEET

Revised: January, 2018

TECHNYL® A 21T3 V25 Black 15N is a Red Phosphorous flame retardant polyamide 66, reinforced with 25% of glass fibre, heat stabilized, impact improved, for injection moulding. This flame retardant grade offers excellent filling qualities and with good mechanical properties. This grade is stabilized to offer a very low migration and corrosion of metallic contacts.

GENERAL

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific	• Europe
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight	
Additive	• Flame Retardant	• Heat Stabilizer
Key Benefits	• Glow Wire Resistance • GWFI 960°C at 0.8 mm thickness • Good Impact Resistance	• Low Phosphine Emission • UL 94 V0 at 0.8 mm
Applications	• Circuit Breaker • Conversion Devices • Electrical protection devices	• Electrical/Electronic Applications • Structural and Casing parts • Switch, Plug, Control & Sockets
Certification/Compliance	• EC 1907/2006 (REACH)	• UL QMFZ2
RoHS Compliance	• RoHS Compliant	
Colors Available	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	
Resin ID (ISO 1043)	• PA66-GF25 FR(52)	

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption				ISO 62
24 hr, 23°C	0.90		%	
Equilibrium, 23°C, 50% RH	2.1		%	
Density	1.31		g/cm³	ISO 1183/A

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	8000	5400	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	130	70	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	2.7	4.0	%	ISO 527-2
Flexural Modulus (23°C)	7900	5200	MPa	ISO 178
Flexural Stress (23°C)	200	155	MPa	ISO 178
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0		kJ/m²	
23°C	7.0	9.0	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60		kJ/m²	
23°C	57	65	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/At
1.8 MPa, Unannealed	230		°C	
Melting Temperature	263		°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (0.800 mm)	37		kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	500		V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.8 mm	V-2			
1.6 mm	V-0			
3.2 mm	V-0			
Glow Wire Flammability Index				IEC
1.6 mm	960		°C	60695-2-12
3.2 mm	930		°C	
Glow Wire Ignition Temperature				IEC
1.6 mm	725		°C	60695-2-13
3.2 mm	800		°C	
Oxygen Index	28		%	ISO 4589-2

PROCESSING

Injection	Dry Unit
Drying Temperature	80 °C
Suggested Max Moisture	0.20 %
Rear Temperature	265 to 275 °C
Middle Temperature	270 to 280 °C
Front Temperature	280 to 290 °C
Mold Temperature	60 to 90 °C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Solvay recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Solvay advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% Chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

Notes

Typical properties: these are not to be construed as specifications.