

TECHNYL® AZ 536 V20 Black is a polyamide blend of polyamide 66 and polyphenyl ethers (PPE), reinforced with 20% of glass fiber, for extrusion. This grade offers a reduced thermal conductivity in comparison to commonly used materials such as polyamide 66 glass fiber reinforced.

GENERAL

Material Status	• Commercial: Active - Private
Availability	• Africa & Middle East • Europe
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Key Benefits	• High Melt Strength • Reduced Thermal Conductivity
Applications	• Consumer and Industrial applications • Window insulation
Certification/Compliance	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
Colors Available	• Black
Forms	• Pellets
Processing Method	• Extrusion
Resin ID (ISO 1043)	• P66+PPE-GF20

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption (24 hr, 23°C)	1.0		%	ISO 62
Density	1.25		g/cm³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7180		MPa	ISO 527-2/1A
Tensile Stress				ISO 527-2/1A
Yield, 23°C	122		MPa	
Break, 23°C	122		MPa	
Tensile Strain				ISO 527-2
Yield, 23°C	2.4		%	
Break, 23°C	2.4		%	
Flexural Modulus (23°C)	5020		MPa	ISO 178
Flexural Stress (23°C)	157		MPa	ISO 178
Charpy Notched Impact Strength (23°C)	6.4		kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	42		kJ/m²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	6.2		kJ/m²	ISO 180

Thermal	Dry	Conditioned Unit	Test Method
Heat Deflection Temperature 0.45 MPa, Unannealed	236	°C	ISO 75-2/Bf
Melting Temperature	262	°C	ISO 11357-3

PROCESSING

Injection	Dry Unit
Drying Temperature	110 °C
Suggested Max Moisture	0.030 %
Rear Temperature	270 to 290 °C
Middle Temperature	270 to 290 °C
Front Temperature	270 to 290 °C
Mold Temperature	270 to 290 °C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -35°C. Recommended time 8h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

Notes

Typical properties: these are not to be construed as specifications.