

TECHNYL® C 218L V30 Black-J is a polyamide 6 reinforced with 30% glass fibre and UV stabilized for injection moulding. The product offers an excellent combination between thermal and mechanical properties.

GENERAL

Material Status	• Commercial: Active
Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer • UV Stabilizer
Key Benefits	• Good Dimensional Stability • Good Mold Release • Good Flow • Good UV Resistance
Applications	• Automotive applications • Interior trims and switches
RoHS Compliance	• RoHS Compliant
Colors Available	• Black • Grey
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GF30

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Water Absorption (24 hr, 23°C)	0.95		%	ISO 62
Density	1.35		g/cm³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9700	6200	MPa	ISO 527-2/1A
Tensile Strength				
Break, 23°C	160		MPa	ASTM D638
Break, 23°C	165	120	MPa	ISO 527-2/1A
Tensile Elongation				
Break, 23°C	3.0		%	ASTM D638
Break, 23°C	3.8	4.5	%	ISO 527-2
Flexural Modulus				
23°C	8500		MPa	ASTM D790
23°C	14300		MPa	ISO 178
Flexural Strength (23°C)	230		MPa	ASTM D790
Charpy Notched Impact Strength (23°C)	8.0		kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70		kJ/m²	ISO 179/1eU
Notched Izod Impact (23°C)	110		J/m	ASTM D256

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220		°C	ISO 75-2/Bf
1.8 MPa, Unannealed	205		°C	ASTM D648
1.8 MPa, Unannealed	202		°C	ISO 75-2/Af
Melting Temperature	222		°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+11	ohms·cm	IEC 60093
Electric Strength (2.00 mm)		22	kV/mm	IEC 60243-1
Relative Permittivity	3.80	4.50		IEC 60250
Comparative Tracking Index (Solution A)	550	475	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.2 mm)	HB			UL 94
Glow Wire Flammability Index (1.6 mm)	650		°C	IEC 60695-2-12
Oxygen Index	23		%	ISO 4589-2

PROCESSING

Injection	Dry	Unit
Drying Temperature	80	°C
Suggested Max Moisture	0.20	%
Rear Temperature	230 to 235	°C
Middle Temperature	235 to 240	°C
Front Temperature	240 to 250	°C
Mold Temperature	60 to 90	°C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

Notes

Typical properties: these are not to be construed as specifications.