



TECHNYL eXten® D 238 V30 BLACK

TECHNICAL DATA SHEET

Revised: April, 2017

TECHNYL eXten® D 238 V30 Black is a polyamide 6.10, reinforced with 30% of glass fibre, heat stabilized, impact modified, for injection moulding. This grade offers excellent chemical resistance, low water absorption, very good mechanical properties and moldability. It is a partially bio-sourced material.

GENERAL

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Key Benefits	• Partially Bio-based • High Chemical Resistance • Heat Stabilized (Inorganic)	• Good Impact Resistance • Low Moisture Absorption	
Applications	• Automotive applications • Fuel connectors	• Fuel lines	
Certification/Compliance	• EC 1907/2006 (REACH)		
RoHS Compliance	• RoHS Compliant		
Colors Available	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA610-GF30		

PROPERTIES

Typical values of properties are for Black grades

Physical	Dry	Conditioned	Unit	Test Method
Molding Shrinkage				ISO 294-4
Across Flow	0.70		%	
Flow	0.30		%	
Water Absorption				ISO 62
24 hr, 23°C	0.34		%	
Saturation, 23°C	1.9		%	
Density	1.25		g/cm ³	ISO 1183/A

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7900	4900	MPa	ISO 527-2/1A
Tensile Stress (Break, 23°C)	115	80	MPa	ISO 527-2/1A
Tensile Strain (Break, 23°C)	4.0	9.0	%	ISO 527-2
Flexural Modulus (23°C)	6500		MPa	ISO 178
Flexural Stress (23°C)	180		MPa	ISO 178
Charpy Notched Impact Strength (23°C)	12		kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	100		kJ/m ²	
23°C	80	100	kJ/m ²	

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	216		°C	ISO 75-2/Bf
1.8 MPa, Unannealed	194		°C	ISO 75-2/Af
Melting Temperature	215 to 220		°C	ISO 11357-3

PROCESSING

Injection	Dry	Unit
Drying Temperature	80	°C
Suggested Max Moisture	0.20	%
Rear Temperature	240 to 250	°C
Middle Temperature	245 to 255	°C
Front Temperature	250 to 260	°C
Mold Temperature	60 to 90	°C

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

MULTIPOINT DATA

Isothermal Stress vs. Strain (ISO 11403-1)

