



TENAC™ 4013A

Asahi Kasei Corporation - Acetal (POM) Homopolymer

Tuesday, February 15, 2022

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Dimensional Stability • Good Weather Resistance	• Homopolymer • Medium Viscosity	• UV Resistant
Uses	• Automotive Interior Parts • Engineering Parts	• Gears • Housings	
Automotive Specifications	• GM GMW19P-POM-H3U		
Part Marking Code (ISO11469) (ISO 11469)	• >POM<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.42	g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.8 to 2.2	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-1
Tensile Stress			
Yield	70.0	MPa	ISO 527-2
--	67.0	MPa	ASTM D638
Tensile Elongation			
Break	45	%	ASTM D638
Break	40	%	ISO 527-2
Flexural Modulus			
--	2900	MPa	ASTM D790
--	2700	MPa	ISO 178
Flexural Strength	98.0	MPa	ASTM D790
Taber Abrasion Resistance	13.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m ²	ISO 179
Notched Izod Impact	85	J/m	ASTM D256

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

TENAC™ 4013A

Asahi Kasei Corporation - Acetal (POM) Homopolymer

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	94		
R-Scale	120		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	172	°C	ASTM D648
0.45 MPa, Unannealed	164	°C	ISO 75-2/B
1.8 MPa, Unannealed	136	°C	ASTM D648
1.8 MPa, Unannealed	102	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696 ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16 to 1.0E+17	ohms	ASTM D257
Volume Resistivity (23°C)	1.0E+15 to 1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Arc Resistance	250	sec	ASTM D495

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
- Do not use plastics in any of the following orally- or medically-related applications.
- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
- For drinking water application, please consult Asahi Kasei Corporation.
- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.