



TENAC™-C GN455

Asahi Kasei Corporation - Acetal (POM) Copolymer

Tuesday, February 15, 2022

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber		
Features	• Copolymer • High Stiffness	• High Strength • Medium Viscosity	
Uses	• Engineering Parts	• Gears	• Housings
Part Marking Code (ISO11469) (ISO 11469)	• >POM-GF25<		

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.59	g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Flow	0.40 to 0.60	%	
Across Flow	1.0 to 1.2	%	
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ISO 527-1
Tensile Stress			
Break	120	MPa	ISO 527-2
--	121	MPa	ASTM D638
Tensile Elongation			
Break	8.0	%	ASTM D638
Break	2.0	%	ISO 527-2
Flexural Modulus			
--	7900	MPa	ASTM D790
--	7500	MPa	ISO 178
Flexural Strength	188	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m ²	ISO 179
Notched Izod Impact	62	J/m	ASTM D256

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

TENAC™-C GN455

Asahi Kasei Corporation - Acetal (POM) Copolymer

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	79		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	166	°C	ASTM D648
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	163	°C	ASTM D648 ISO 75-2/A
CLTE			
Flow	4.0E-5	cm/cm/°C	ASTM D696
Flow	4.0E-5 to 9.0E-5	cm/cm/°C	ISO 11359-2
Transverse	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	HB		
1.5 mm	HB		

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
- Do not use plastics in any of the following orally- or medically-related applications.
- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
For drinking water application, please consult Asahi Kasei Corporation.
- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.