



TENAC™-C ZLV40

Asahi Kasei Corporation - Acetal (POM) Copolymer

Tuesday, February 15, 2022

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Lubricant		
Features	• Copolymer • Low Friction	• Low VOC • Lubricated	• Medium Viscosity • Wear Resistant
Uses	• Automotive Applications • Engineering Parts	• Gears • Housings	
Automotive Specifications	• GM GMW22P-POM-C2DS		
Part Marking Code (ISO11469) (ISO 11469)	• >POM+SI<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity			
--	1.39	g/cm ³	ASTM D792
--	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-1
Tensile Stress			
Yield	61.0	MPa	ISO 527-2
--	56.0	MPa	ASTM D638
Tensile Elongation			
Break	25	%	ASTM D638
Break	20	%	ISO 527-2
Flexural Modulus	2600	MPa	ASTM D790 ISO 178
Flexural Strength	89.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.0	kJ/m ²	ISO 179
Notched Izod Impact	56	J/m	ASTM D256

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

TENAC™-C ZLV40

Asahi Kasei Corporation - Acetal (POM) Copolymer

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	86		
R-Scale	117		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	157	°C	ASTM D648 ISO 75-2/B
1.8 MPa, Unannealed	100	°C	ASTM D648 ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696 ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.79 mm)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
- Do not use plastics in any of the following orally- or medically-related applications.
- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
For drinking water application, please consult Asahi Kasei Corporation.
- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.