



Thermylene® P-40TC-8100

Asahi Kasei Plastics North America Inc. - Polypropylene

Wednesday, July 29, 2015

General Information

Product Description

PP-TD40
40% Talc Reinforcement

General

Filler / Reinforcement	• Talc, 40% Filler by Weight
Automotive Specifications	• CHRYSLER MS-DB-500 CPN 3549 • GM GMP.PP.030 Color: Black

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	4640	psi	ISO 527-2
Flexural Modulus	638000	psi	ISO 178
Flexural Stress	7400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.1	ft-lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (66 psi, Unannealed)	275	°F	ISO 75-2/B
Heat Deflection Temperature (264 psi, Unannealed)	187	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.