

Thermylene® P7-30FG-0790

Asahi Kasei Plastics North America Inc. - Polypropylene

General Information			
Product Description			
PP-GF30 30% Glass Fiber Reinforcement			
General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		

ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	12500	psi	ISO 527-2
Flexural Modulus	885000	psi	ISO 178
Flexural Stress	19000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.8	ft-lb/in²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	291	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.