

Versaflex™ PKG 4465 T CN

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ PKG 4465 T CN is an easy processing, general purpose TPE designed for a wide variety of applications.

General

Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Features	• Chemical Resistant • General Purpose • Good Processability • Oil Resistant
Uses	• General Purpose • Medical/Healthcare Applications • Overmolding • Soft Touch Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	0.880 g/cm ³	0.880 g/cm ³	ISO 1183
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength			DIN 53504
Break, 0.0787 in (2.00 mm)	798 psi	5.50 MPa	
Tensile Elongation			DIN 53504
Break, 0.0787 in (2.00 mm)	490 %	490 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A, 10 sec)	65	65	ISO 48-4
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ISO 11443
392°F (200°C), 11200 sec ⁻¹	26.3 Pa·s	26.3 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	329 to 392 °F	165 to 200 °C
Middle Temperature	365 to 464 °F	185 to 240 °C
Front Temperature	370 to 455 °F	188 to 235 °C
Nozzle Temperature	370 to 446 °F	188 to 230 °C
Mold Temperature	60 to 113 °F	16 to 45 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	0.00 to 120 psi	0.00 to 0.827 MPa

Notes

¹ Typical values are not to be construed as specifications.

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com

Copyright ©, 2023 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.