

Technical Data Sheet

Vitamide AY16BK 1768/1



Polyamide 66

Product Description


Flame retardant V0, 30% Glass filled Polyamide 66. This Grade offers a good balance of flow, tensile, flexural and impact strength. Available with enhanced UV (AY26), heat stability (AY36) Oil heat glycol hydrolysis resistance (AY66), UV and heat resistance (AY76), and hydrolysis resistance (AY86). Colour matched compounds and customer specific performance requirements are available on request

Regulatory Status

For regulatory compliance information, see *Vitamide* AY16BK 1768/1 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Limited Issue
Availability	Africa-Middle East; Asia-Pacific; Europe; Latin America; North America
Processing Method	Injection Molding
Additive	Flame Retardant
Filler/Reinforcement	Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.59	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break	3	%	ISO 527-2
Flexural Modulus	7500	MPa	ISO 178
Tensile Stress at Break	155	MPa	ISO 527-2
Flexural Stress	175	MPa	ISO 178
Impact			
Notched Izod Impact Strength	7	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa)	240	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	200	°C	ISO 75-2/A
DSC Melting Point	260	°C	ISO 3146
Electrical			
Tracking Resistance (DIN 53480) (DIN 53480)			
Flammable			
Burning Rate, (FMVSS 302)	<100	mm/min	FMVSS 302
Glow Wire Flammability Index	960	°C	IEC 60695-2-12
Oxygen Index	31	%	ISO 4589-2
Additional Information			
Molding Shrinkage	0.35	%	ISO 294-4
Water Absorption 24h/23C	1.1	%	ISO 62
UL Information			
Flame Rating, (1.6 mm)	V-0		UL 94



Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	60 to 120	°C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.