

Technical Data Sheet

Vitamide BF30WT6781 WHI



Polyamide 6

Product Description

Vitamide BF30WT6781 WHI is a Polyamide 6 material and is typically used in Injection Molding applications.

Regulatory Status

For regulatory compliance information, see Vitamide BF30WT6781 WHI [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Limited Issue
Availability	Asia-Pacific; Europe
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.24	g/cm ³	ISO 1183
Viscosity Number, (96% H ₂ SO ₄ (Sulphuric Acid))	145	cm ³ /g	ISO 307
Mechanical			
Tensile Stress at Yield			
(Type 1A, 50 mm/min)	65.0	MPa	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	40.0	MPa	ISO 527-2
Nominal Tensile Strain at Break			
(50 mm/min, Type 1A) - Conditioned	140	%	ISO 527-2
(50 mm/min, Type 1A)	35	%	ISO 527-2
Tensile Strain at Break			
(Type 1A, 50 mm/min)	65	%	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	40	%	ISO 527-2
Flexural Modulus, (2.0 mm/min)	3500	MPa	ISO 178
Tensile Strain at Yield			
(Type 1A, 50 mm/min)	3.5	%	ISO 527-2
(Type 1A, 50 mm/min) - Conditioned	25	%	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	3800	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	1600	MPa	ISO 527-1
Flexural Stress			
(2.0 mm/min, 6.5%)	110	MPa	ISO 178
(2.0 mm/min, 5.5%)	115	MPa	ISO 178
(Type 1A, 2.0 mm/min, 3.5%)	105	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	50	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	45	kJ/m ²	ISO 179

Thermal

Vicat Softening Temperature			
(B (50N), 50 °C/h)	190	°C	ISO 306
(A (10N), 50 °C/h)	215	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	185	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	70	°C	ISO 75-2/A

Electrical


Comparative Tracking Index (CTI), (Solution A)	550	V	IEC 60112
--	-----	---	-----------

Flammable

Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
Glow Wire Flammability Index			
(0.75 mm)	960	°C	IEC 60695-2-12
(1.5 mm)	960	°C	IEC 60695-2-12
(3.0 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			
(0.75 mm)	775	°C	IEC 60695-2-13
(1.5 mm)	775	°C	IEC 60695-2-13
(3.0 mm)	775	°C	IEC 60695-2-13

UL Information

Flame Rating		
(1.6 mm)	V-2	UL 94
(3.2 mm)	V-2	UL 94
(0.8 mm)	V-2	UL 94
Flammability Classification		
(0.8 mm)	V-2	IEC 60695-11-10, -20
(1.6 mm)	V-2	IEC 60695-11-10, -20
(3.2 mm)	V-2	IEC 60695-11-10, -20

**Injection Parameters**

	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C

Suggested Max Moisture	0.040 to 0.10	%
Screw Speed	<250	mm/sec
Processing (Melt) Temp	240 to 260	°C
Injection Rate	Slow-Moderate	
Mold Temperature	60 to 100	°C

Notes

These are typical property values not to be construed as specification limits.

Processing notes

Melt contacting surfaces should be made of a high quality, corrosive resistant steel. Positive experiences have been made with steel qualities containing > 12% chromium.

Avoid processing at very barrel high temperatures or above the recommended melt temperature range as this can increase risk of deposit onto the tool surfaces. Avoid long residence times. At start and end of production, it is recommended to purge clean with non-flame retardant polymer or a polyolefin.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.